

Hiperprime®

Highly chemical resistant topcoat for thermal transfer printing

Characteristics

- + Base materials: PET and PP all common thicknesses
- + Available width: 1,020 (40.16 ") & 1,550 mm (61.02 ")
- + Design options: clear, white, silver, coloured
- + Surface finish: glossy, semi-matt, matt, customized finishes available
- + Topcoat printability: thermal transfer - wax, wax/resin, resin ribbon; best performance is obtained with Ricoh B110CU or 3M 92904 resin ribbon; UV-flexo (subject to customer evaluation)



Key Advantages

- + No overlam is required
- + Readability of the print is ensured even after contact with fuel, solvents and other chemicals
- + Combination with a wide range of VOID and security label technologies

Interested?

We are happy to provide you with detailed advice.

Markus Brezina
Sales Director Labeling

T +43 7269 7570-170
M +43 664 961 78 71
M.Brezina@hueck-folien.at

Joachim Ortner
Sales Manager Labeling

T +43 7269 7570-162
M +43 664 961 78 78
J.Ortner@hueck-folien.at

Johann Hilburger
Sales Manager Labeling

T +49 961 388 337-11
M +49 160 906 138 55
J.Hilburger@hueck-folien.de



Hiperprime®

by Hueck Folien

for thermal transfer printing

Performance of Hiperprime®

when printed with Ricoh B110CU thermal transfer ribbon on a 300dpi ZEBRA ZM4+ flat head printer

Substance	Number of rubs (back & forth)	Performance
Ethanol	250	+++
IPA	250	+++
Unleaded petrol (SP95)	85	++
Diesel	250	+++
Brake Fluid	250	+++
Motor Oil	250	+++
Windshield washer	250	+++
MEK	185	++
Xylene	250	+++
Toluene	250	+++
Acetone	250	+++
Thinner	250	+++
Hexane	250	+++
Scratch rubber	50	+++
Smear & Heat 100°C	50	+++
Water 24 hours	n.a.	+++
Light 73 hours	n.a.	+++

+++ Good ++ Average + Bad

Test conditions available on request

Visit our
website!



Hiperprime®