



# Hiperprime®

## Highly chemical resistant topcoat for thermal transfer printing

### Characteristics

- + Available widths: 1,020 (40.16") & 1,550 mm (61.02")
- + Base materials / thicknesses: PET 12 - 75 µm (0.47 – 2.95 mil), PP 30 - 50 µm (1.18 – 1.97 mil)
- + Design options: clear, white, silver, coloured
- + Topcoat printability: thermal transfer - wax, wax/resin, resin ribbons; best performance is obtained with Ricoh B110CU or 3M 92904 resin ribbon; UV-flexo (subject to customer evaluation)



### Key Advantages

- + No overlam is required
- + Readability of the print is ensured even after contact with fuel, solvents and other chemicals
- + Customizable VOID pattern, holograms, security printing
- + Surface finish: glossy, semi-matt, matt, customized finishes available

### Interested?

We are happy to provide you with detailed advice.

Reinhard Kammerhuber  
Sales Director Labeling

T +43 7269 7570-160  
M +43 664 961 78 70  
R.Kammerhuber@hueck-folien.at

Joachim Ortner  
Sales Manager Labeling

T +43 7269 7570-162  
M +43 664 961 78 78  
J.Ortner@hueck-folien.at

Johann Hilburger  
Sales Manager Labeling

T +49 961 388 337-11  
M +49 160 906 138 55  
J.Hilburger@hueck-folien.de

Visit our  
website!





# Hiperprime®

# by Hueck Folien

## for thermal transfer printing

Performance of Hiperprime® on PET 50 µm white:  
when printed with Ricoh B110CU thermal transfer ribbon on a 300dpi ZEBRA ZM4+ flat head printer

Substance	Number of rubs (back & forth)	Performance
Ethanol	250	+++
IPA	250	+++
Unleaded petrol (SP95)	85	++
Diesel	250	+++
Brake Fluid	250	+++
Motor Oil	250	+++
Windshieldwasher	250	+++
MEK	185	++
Xylene	250	+++
Toluene	250	+++
Acetone	250	+++
Thinner	250	+++
Hexane	250	+++
Scratch rubber	50	+++
Smear & Heat 100°C	50	+++
Water 24 hours	n.a.	+++
Light 73 hours (Xenon)	n.a.	+++

Test conditions available on request

+++ Good    ++ Average    + Bad

### Interested?

We are happy to provide you with detailed advice.

Reinhard Kammerhuber  
Sales Director Labeling

Joachim Ortner  
Sales Manager Labeling

Johann Hilburger  
Sales Manager Labeling

T +43 7269 7570-160  
M +43 664 961 78 70  
R.Kammerhuber@hueck-folien.at

T +43 7269 7570-162  
M +43 664 961 78 78  
J.Ortner@hueck-folien.at

T +49 961 388 337-11  
M +49 160 906 138 55  
J.Hilburger@hueck-folien.de

# Hiperprime®